

Dimensional Data are Subject to Manufacturing Tolerance and Change Without Notice

**PLAIN END PIPE. 3 METERS LENGTH**

Size	Wt/Piece(Kgs)	Pieces/Bundle	Kgs/Bundle	Qty/40'	Qty/40'
50	13.00	70	910.0	26	1820
70	17.70	70	1239.0	26	1820
75	18.90	50	945.0	26	1300
100	25.20	38	957.6	26	988
125	35.40	23	814.2	26	598
150	42.20	20	844.0	26	520
200	69.30	10	693.0	26	260
250	99.80	8	798.4	26	208
300	129.70	6	778.2	26	156

**DIMENSIONS AND TOLERANCES**

Size	OD	Tolerance	Normal T	Minimum T	Length
50	58	+2/-1	3.5	3.0	3000+/-20
70	78	+2/-1	3.5	3.0	3000+/-20
75	83	+2/-1	3.5	3.0	3000+/-20
100	110	+2/-1	3.5	3.0	3000+/-20
125	135	+2/-1	4.0	3.5	3000+/-20
150	160	+2/-2	4.0	3.5	3000+/-20
200	210	+2.5/-2.5	5.0	4.0	3000+/-20
250	274	+2.5/-2.5	5.5	4.5	3000+/-20
300	326	+2.5/-2.5	6.0	5.0	3000+/-20

Minimum tensile strength 200 MPa  
Minimum ring crush strength 350 Mpa  
Maximum Brinell hardness 260 HB

**Straightness of Pipes**

0.15% of their length of nominal sizes greater than DN70;  
0.20% of their length of nominal sizes equal to or less than DN70.

**End faces**

3° for nominal sizes DN40 to DN200  
2° for nominal sizes DN250 to DN 600

**Hydraulic Pressure Test:**

0.45Mpa

**Packing**

Solid Wood Pallet

**Richang Qiaoshan Trade Co., Ltd.**  
1-256, No. 35 Zhenxing Road, Changping, Beijing, China 102200  
Ph: 86-10- 64644308 Fax: 86-10-64644308  
[www.qiaoshan.co](http://www.qiaoshan.co)

Date: Aug-24  
Dwg. No. : **EN877**