


Dimensional Data are Subject to Manufacturing Tolerance and Change Without Notice



단위 : mm

호칭 지름	관 두께	실 안지름	실 바깥지름	무 게(kg) 유효 길이 (L)=3000
	Т	D_1	<i>D</i> ₂	
50	3.5	51	58	15.0
75	3.5	76	84	20.5
100	3.5	103	110	28.0
125	4.0	127	135	35.4
150	4.0	153	160	42.2
200	5.0	202	213	69.3

Minimum tensile strength 200 MPa Minimum ring crush strength 350 Mpa Maximum Brinell hardness 260 HB

Straightness of Pipes

0.15% of their length of nominal sizes greater than DN70;0.20% of their length of nominal sizes equal to or less than DN70.

End faces

3° for nominal sizes DN40 to DN200 2° for nominal sizes DN250 to DN 600

Hydraulic Pressure Test:

0.45Mpa

Packing

Solid Wood Pallet

Richang Qiaoshan Trade Co., Ltd.	Date:	Aug-24
1-256, No. 35 Zhenxing Road, Changping, Beijing, China 102200		
Ph: 86-10- 64644308 Fax: 86-10-64644308	Dwg. No. :	KS D 4307 Class 2
www.qiaoshan.co		