

Dimensional Data are Subject to Manufacturing Tolerance and Change Without Notice

NO HUB PIPE. 10' LAYING LENGTH

Size	Wt/Piece(Kgs)	Wt/Piece(Lbs)	Pieces/Bundle	Kgs/Bundle	Lbs/Bundle
1 1/2"	13.0	29	84	1092	2407
2"	16.3	36	68	1108	2444
3"	23.5	52	44	1034	2280
4"	33.5	74	30	1005	2216
5"	42.6	94	21	895	1972
6"	51.0	112	18	918	2024
8"	82.2	181	10	822	1812
10"	130.0	287	8	1040	2293
12"	148.0	326	6	888	1958
15"	241.8	533	3	725	1599

DIMENSIONS AND TOLERANCES

Size	Wt/Piece(Lbs)	ID	OD	Norm T	Min T
1 1/2"	29	1.50±.06	1.90±.06	0.16	0.13
2"	36	1.96±.09	2.35±.09	0.16	0.13
3"	52	2.96±.09	3.35±.09	0.16	0.13
4"	74	3.94±.09	4.38+.09/-.05	0.19	0.15
5"	94	4.94±.09	5.30+.09/-.05	0.19	0.15
6"	112	5.94±.09	6.30+.09/-.05	0.19	0.15
8"	181	7.94±.13	8.38+.13/-.09	0.23	0.17
10"	287	10.00±.13	10.56±.09	0.28	0.22
12"	326	11.94±.13	12.50±.13	0.28	0.22
15"	533	15.11±.13	15.83±.13	0.35	0.3

Mechanical Properties

Tensile Strength not less than 21000psi (145Mpa).

Straightness of Pipes

Deflections not exceed 5/8"(16mm).

Hydraulic Pressure Test:

0.45Mpa (65psi)

Coating

Interior: Epoxy Asphalt Paint.

Exterior: Asphalt Paint.

Packing

Solid Wood Pallet

Richang Qiaoshan Trade Co., Ltd.

1-256, No. 35 Zhenxing Road, Changping, Beijing, China 102200

Ph: 86-10- 64644308 Fax: 86-10-64644308

www.qiaoshan.co

Date: Aug-24

Dwg. No. : **ASTM A 888**